

Our Ref: SW/LS

10 March 2021

Report 372361

Page 1 of 3

Abitex SRL (part of AURIM SPA Group)
CADONEGHE (PD)
VIA E. FERMI
35010
Italy

Contact: Matteo Bortolossi

DATE RECEIVED	:	04 MARCH 2021
DATE TESTED	:	10 MARCH 2021
QUALITY REFERENCE	:	HORO
SUPPLIER	:	ABITEX SRL
COLOUR / DESIGN	:	000
REPUTED FIBRE CONTENT	:	100% POLYESTER
FABRIC DESCRIPTION	:	WOVEN
END-USE	:	UPHOLSTERY/CURTAINS
ORDER NUMBER	:	9/11

REQUEST: BS 5852:2006 "Methods of Test for the Assessment of the ignitability of upholstered seating by smouldering and flaming ignition sources" using ignition source 5 (wood crib)

RESULT: The sample meets the flammability performance requirements of BS 5852:2006 when tested using ignition source 5 (wood crib)



S. WISEMAN
LABORATORY DIRECTOR



L. SMITH
FLAMMABILITY TECHNICIAN

This report shall not be reproduced except in full without written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



FIRE TESTS ACCORDING TO BS 5852:2006. Methods of Test for the Assessment of the ignitability of upholstered seating by smouldering and flaming ignition sources.

Conditioning

Prior to testing, the sample was placed in indoor ambient conditions for 72 hours and then conditioned for 24 hours in an atmosphere having a temperature of $23 \pm 2^{\circ}\text{C}$ and a relative humidity of $50 \pm 5\%$.

Procedure

Specimens of 'Horo' were mounted over fillings of combustion modified high resilience foam at a density of approximately 50 Kg/m^3 , and tests were made using ignition source 5. Pass classifications were assigned if the performance requirements stated below were met.

Requirements

<u>Ignition Source No.</u>	<u>Maximum duration allowed for progressive smouldering</u>	<u>Maximum duration allowed for flaming</u>
5	60 min after ignition of wood crib	10 min after ignition of wood crib

The following test results relate only to the ignitability of the combination of upholstery composites (BS5852: 2006, Clause 11) under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

They also only relate to the materials tested. They do not guarantee to represent the performance of production materials.

	<u>Test 1</u>	<u>Test 2</u>
Time of flame extinction (min/secs)	3/36	8/12
Progressive smouldering	No	No
Damage through full thickness	No	No
Result designation	NI (non-ignition)	NI (non-ignition)

Comments

An 'NI' designation indicates that the sample met the flammability performance requirements of BS 5852:2006 when tested using ignition source 5 (wood crib).

Decision rules

The decision rule applicable to statements of conformity relating to the test(s) carried out is simple acceptance based on the measured test results not falling within a range either side of a specified limit that is equal to the uncertainty of measurement for the parameter measured (based on 95% confidence levels). In all other regards, the decision rule is based on simple acceptance predicated upon the conditions of testing falling within the criteria for test set out in the test method with a conformance probability of 95%. The risk of false accept or false reject is therefore not greater than 2.5%.

Uncertainty of measurement:	Timings	$\pm 0.4\text{s}$
	Dimensions	$\pm 0.5\text{mm}$

Our Ref: SW/LS

10 March 2021

Report 372361

Page 3 of 3

