

abitex

abitex srl
via del cristo 84
33044 manzano
ud - italy

t +39 0432 746060
www.abitex.eu
info@abitex.eu

grisù 04038



IT
codice doganale
54072011.

utilizzo
tende, imbottiti, assorbimento acustico.

caratteristiche
68% poliestere - 32% polipropilene,
altezza cm \pm 140, peso \pm 400 gr/m².

tintura
il prodotto è tinto in massa, il prodotto è tinto in filo.

lunghezza pezza
circa 35 mtl., disponibile anche al taglio con maggiorazione.

abrasione
> 135.000 cicli, ISO 12947-2.

solidità alla luce
> 6, ISO 105 B02.

solidità allo sfregamento
secco 4/5, umido 4, ISO 105 X12.

resistenza alla cucitura
ordito 3 mm, trama 3 mm, ISO 13936-2.

pilling
4/5, ISO 12945-2.

assorbimento acustico
 α_w 0,75 arricciato; α_w 0,60 teso;
ISO 354 - allestimento G.

resistenza al fuoco
1IM - UNI 9175; Class 1 - UNI 9177; EN 1021 1/2;
NF D 60 013 (AM 18); DIN 4102 B1; NFPA 260 Class 1;
California TB 117-2013;
IMO MED 3.20 - FTP Code 307 part 8; ÖNORM B 3825.

resistenza al fuoco,
solo su richiesta con trattamento
BS 5852 crib 5.

attenzione
sono ammesse leggere differenze di colore tra differenti
partite. le schede tecniche vengono costantemente
aggiornate sul sito, pertanto vi invitiamo a verificare online i
dati del prodotto su www.abitex.eu

EN
customs code
54072011.

use
curtains, upholstered furniture, sound absorption.

features
68% polyester - 32% polypropylene,
width cm \pm 140, weight \pm 400 g/m².

dyeing
solution dyed product, yarn dyed product.

roll length
approx. 35 lm., can also be cut-to-length at an extra cost.

abrasion resistance
> 135.000 rubs, ISO 12947-2.

colour fastness to light
> 6, ISO 105 B02.

fastness to rubbing
dry 4/5, wet 4, ISO 105 X12.

seam slippage
warp 3 mm, weft 3 mm, ISO 13936-2.

pilling
4/5, ISO 12945-2.

sound absorption
 α_w 0,75 folded; α_w 0,60 not folded;
ISO 354 - G type.

fire resistance
1IM - UNI 9175; Class 1 - UNI 9177; EN 1021 1/2;
NF D 60 013 (AM 18); DIN 4102 B1; NFPA 260 Class 1;
California TB 117-2013;
IMO MED 3.20 - FTP Code 307 part 8; ÖNORM B 3825.

fire resistance, only on request with treatment
BS 5852 crib 5.

attention
slight colour differences between different batches are
allowed. as technical data sheets are updated from time to
time, we invite you to verify the latest document published for
each item on the website www.abitex.eu



fireproof



imo-med



sound
absorbent



year
guarantee