

**MESSRS.:  
ABITEX SRL  
VIA CASALI 48  
33048 SAN GIOVANNI AL  
NATISONE (UD)  
ITALIA**

<b>REPORT NR.</b>	<b>1601842-002</b>
<b>REPORT DATE</b>	<b>12/05/2016</b>
ACCEPTANCE DATE	09/05/2016
START TEST DATE	09/05/2016
END TEST DATE	12/05/2016
SAMPLING BY CUSTOMER	

## TEST REPORT

SAMPLE DESCRIPTION: 02038 002 140 401 NABUCCO PLUS 401 P.TA 161127601 0164035

TEST	M.U	RESULTS	EXPANDED UNCERTAINTY <sup>1</sup>
------	-----	---------	-----------------------------------

**6012061 Assessment of the ignitability of upholstery fabric - Cigarette**

Method: EN 1021-1:2014

Test 1 - Combustion with flame	0"
Test 1 - Progressive smouldering	0"
Test 1 - Result	N.I.
Test 2 - Combustion with flame	0"
Test 2 - Progressive smouldering	0"
Test 2 - Result	N.I.

Filling material: PU FR HR30S (30-33 Kg/m<sup>3</sup>) supplied by the laboratory.  
Pretreatment: None

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; Acclimatization: At least 16 hours at 20 ± 5 °C e 50 % ± 20 % RH; Ignition source (i.s.): Ignition source 0 - Smouldering cigarette; Maps of results:

- N.I. - Not ignited (Pass the test);  
- IO - Burn with Cigarette 0 (Fail the test).

**(\*) = the tests marked with asterisk are not accredited by Accredia.**

<sup>1</sup> U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

LANARTEX di Rosati Patrizia C. Sas ; Via I° Maggio,27 – 59013 Oste - Montemurlo (PO)  
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

		<b>REPORT NR.</b>	<b>1601842-002</b>
		<b>REPORT DATE</b>	<b>12/05/2016</b>
<b>TEST</b>	<b>M.U.</b>	<b>RESULTS</b>	<b>EXPANDED UNCERTAINTY <sup>1</sup></b>

## 6012071 Assessment of the ignitability of upholstery fabric - Match

Method: EN 1021-2:2014

Test 1 - Combustion with flame	2"
Test 1 - Progressive smouldering	10"
Test 1 - Result	N.I.
Test 2 - Combustion with flame	1"
Test 2 - Progressive smouldering	12"
Test 2 - Result	N.I.

Filling material: PU FR HR30S (30-33 Kg/m<sup>3</sup>) supplied by the laboratory.  
Pretreatment: None

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, and in 1989, 1993 and 2010, Schedule 5 - Part 1 (i.s. 1); Acclimatization: At least 16 hours at 20 ± 5 °C e 50 % ± 20 % RH; Ignition source (i.s.): Ignition source 1 - Match equivalent flame: Maps of results:

- N.I. - Not ignited (Pass the test);  
- I1 - Burn with Match 1 (Fail the test).

Unrepeatable tests to exhaustion test material.

The sample name and, when relevant, its description, are given by the orderer, and LANARTEX does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer. The use of ILAC-ACCREDIA brands is limited by the terms of the agreement ACCREDIA-LANARTEX.

### END OF REPORT

**Managing Director**

Patrizia Rosati



(\*) = the tests marked with asterisk are not accredited by Accredia.

<sup>1</sup> U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

LANARTEX di Rosati Patrizia C. Sas ; Via I° Maggio,27 – 59013 Oste - Montemurlo (PO)  
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it